

# WAKOL Z 675 Levelling Compound

## Technical Information

### Area of application

Self-levelling, cement-based levelling compound for smoothing out unevenness in layer thickness of 1 - 10 mm underneath

- Textile flooring
- Elastic flooring

indoors.

### Special properties



- chromate reduced according to REACH
- suitable for chair castors from a layer thickness of 1 mm
- can be applied with a raket
- self-levelling
- can be pumped

- 1) Based on the criteria of GEV (Association for Emission-controlled Laying Materials), classified as EMICODE EC1 PLUS: very low in emissions
- 2) With the "Blue Angel" label for low emission laying materials according to RAL DE – UZ 113
- 3) Emissions class according to French law
- 4) Cement-based products, low chromate
- 5) Meets the requirements of the European Community
- 6) Suitable for underfloor heating
- 7) Suitable for exposure to castor wheels

### Technical data

Raw material base:

Special cement/quartz mixture with special plastic additives

Material composition:

Special cements  
Mineral fillers  
Redispersible polymer powder  
Additives

Strength of coating:	undiluted processing up to 10 mm
Mixture:	approx. 6,0 l water + 25 kg WAKOL Z 675
Processing time:	approx. 30 minutes
Suitable for walking:	after approx. 3 hours
Waiting time before laying:	up to 2 mm layer thickness, after 24 hours up to 5 mm layer thickness, after 48 hours up to 10 mm layer thickness, after 72 hours
Storage time:	6 months; store in a cool and dry location, tightly seal any opened bags and use as soon as possible
Classification acc. to EN 13813:	CT-C25-F6

### Application and consumption<sup>8)</sup>

Trowel or rakel approx. 1,5 kg/m<sup>2</sup>/mm

8) Consumption is dependent on surface structure and absorbability of subfloor.

## Subfloors

The subfloor as well as the room climate conditions must meet the requirements of the applicable standards and data sheets. Subfloors must be permanently dry, solid, level, free from cracks, dirt and adhesion-inhibiting substances. Use a suitable mechanical procedure to remove separating layers.

Prime cement paving, calcium sulphate concrete, concrete and other absorbent subfloors with WAKOL D 3004 Primer Concentrate, diluted 1:2 with water, or with WAKOL D 3003 Dispersion Primer. Always comply with primer drying times.

New, well sanded, standardised cast asphalt concrete does not require a primer. Prime worn and poorly sanded cast asphalt concrete (according to standard) with WAKOL D 3004 Primer Concentrate, diluted 1:1 with water, or with WAKOL D 3003 Dispersion Primer.

## Usage

WAKOLZ 675 Objektspachtelmasse in einem sauberen Anrührgefäß mit ca. 6 l klarem, kaltem Leitungswasser klumpenfrei anrühren. Drehzahl des Rührgerätes max.600 U/min. Stir WAKOL Z 675 Levelling Compound in a clean stirring vessel with approx. 6,0 l clear, cold tap water until free of lumps. The mixing device must not exceed 600 rpm. After leaving to stand for approx. 2 - 3 minutes, briefly mix the compound again. Apply stirred compound with dripper, smoothing trowel or knife uniformly to the subfloor in the desired layer thickness. Before applying the levelling compound, check whether a sufficiently sized edge strip is available.

Protect the levelling compound layer from direct sunlight and draughts while it sets.

## Work an environmental safety

Keep out of the reach of children. Wear waterproof and hard-wearing protective gloves, goggles and long trousers! Ensure sufficient ventilation during use and drying! Avoid eating, drinking and smoking while applying the product and wear protective gloves. Immediately and thoroughly rinse eyes and skin with water in case of contact. Avoid prolonged skin contact with the installation product. Clean affected areas of skin straight away with water. The longer fresh installation product remains on your skin, the greater the risk of serious damage to the skin. If the installation product comes into contact with your eyes, wash your eyes out with water straight away and see an ophthalmologist. Clean tools with soap and water immediately after use. Do not allow product to enter the sewage system, bodies of water or the ground. Keep children away from fresh installation product!

Storage conditions: Store in a dry and cool place. Opened bags must be sealed airtight immediately.

Information for allergic persons is available at +49 (0)6331/8001-311.

## Disposal

Only empty containers are suitable for recycling. Dried material residue may be disposed of as household waste.

## Important

Processing not below floor temperature of +15 °C and room temperature of +18 °C, as well as room humidity preferably between 40 % and 65 %, maximum 75 %. All information is based on approx. 20 °C and 50 % relative air humidity.

Warm up all laying materials in due time in heated room.

Observe 2 mm minimum layer thickness on non-absorbent subfloors.

WAKOL Z 675 Levelling Compound is not suitable for subsequent parquet bonding.

For applying levelling compound on wooden subfloors that are rigidly bolted or glued to the subfloor, only use WAKOL Z 610 Levelling Compound, dust-reduced, WAKOL Z 615 Levelling Compound, dust-reduced, WAKOL Z 625 Levelling Compound, WAKOL Z 630 Levelling Compound or WAKOL A 830 Levelling Compound in combination with WAKOL AR 114 Reinforcement Fibres.

We guarantee the uniform high quality of our products. All data is based on tests and many years of practical experience and refers to standardised conditions. The variety of materials used and the different construction site conditions, which lie beyond our control, preclude any claims based on this data.

We therefore recommend making sufficient trials. Accompanying flooring manufacturer's instructions and the current national standards must be observed. We gladly provide technical advice.

This Technical Information of 19.02.2024 supersedes all previous versions.

Wakol GmbH  
Bottenbacher Straße 30  
D-66954  
Pirmasens  
Tel. +49 6331 8001 131  
Fax +49 6331 8001 890  
www.wakol.com



Wakol GmbH  
Industriestraße 5  
A-6841  
Mäder  
Tel. +43 5523 64 700  
Fax +43 5523 64 700 64  
www.wakol.at

Wakol Adhesa AG  
Schützengasse 28  
CH-9410  
Heiden  
Tel. +41 31 9210 755  
Fax +41 31 9212 968  
www.wakoladhesa.ch

Wakol Foreco srl  
A Via Kennedy 75  
I-20010  
Marcallo con Casone  
Tel. +39 02 9761 939  
Fax +39 02 97 253 021  
www.wakolforeco.it

Loba-Wakol Polska Sp.z o.o.  
ul. Sławęcińska 16, Macierzysz  
PL-05-850  
Ożarów Mazowiecki  
Tel. +48 22 436 24 20  
Fax +48 22 436 24 21  
www.loba-wakol.pl

Lecol Chemie B.V.  
Schutweg 6  
NL-5145 NP  
Waalwijk  
Tel. +31 416 566 540  
Fax +31 416 566 531  
www.lecol.nl